

V1160

High Density Polyethylene (HDPE) / Injection Molding

PRODUCT DESCRIPTION

V1160 is a High Density Polyethylene (HDPE) with the characteristic of high melt flow rate. It is designed for injection molding processing such as caps & closures, container, pail and housewares.

INDUSTRY

- Caps and Closures
- Container and Pail
- Housewares

PRODUCT FEATURE

- Good impact strength
- Good rigidity
- High melt flow rate

REGULATION COMPLIANCE

- FDA US 21 CFR 177.1520
- Commission Regulation (EU) No. 10/2011
- RoHS Directive 2011/65/EU
- REACH Regulation (EC) No. 1907/2006

PHYSICAL PROPERTY	TEST METHOD	UNIT	VALUE
Melt Flow Rate (190°C/2.16 kg)	ASTM D 1238	g/10 min	15
Melt Flow Rate (190°C/5 kg)	ASTM D 1238	g/10 min	47
Density (23°C)	ASTM D 792	g/cm ³	0.957
Mold Shrinkage	IRPC	%	1.3 – 2.8
MECHANICAL PROPERTY			
Tensile Strength at Yield (1 mm, 50 mm/min, type IV)	ASTM D 638	MPa	29
Tensile Strength at Break (1 mm, 50 mm/min, type IV)	ASTM D 638	MPa	14
Elongation at Break (1 mm, 50 mm/min, type IV)	ASTM D 638	%	130
Charpy Notched Impact Strength (4 mm, 23°C)	DIN 53453	mJ/mm ²	2.5
HARDNESS PROPERTY			
Hardness Shore D (4 mm)	DIN 53505	Shore D	62
THERMAL PROPERTY *Condition B, F50			
Vicat Softening Temperature (4 mm, 10 N, 50 °C)/h	ASTM D 1525	°C	120
Environmental Stress Cracking Resistance (ESCR)*	ASTM D 1693	Hours	3

Conversion (1 MPa = 10.2 kgf/cm² | 1 J/m = 0.1 kgf-cm/cm)

Remark: The values presented above are typical laboratory, not to be construed as specifications and may vary within moderate ranges. The applicability or accuracy of this information or the suitability of our products cannot be guaranteed because users' conditions of use are beyond our control. (Specimen prepared by the IRPC's laboratory with compression process).

V1160

High Density Polyethylene (HDPE) / Injection Molding

PROCESSING TECHNIQUE

Cylinder Temperature	190 – 240 °C
Mold Temperature	50 – 80 °C
Injection Pressure	30 – 80 % of maximum pressure
Holding Pressure	Relative to injection pressure
Back Pressure	0 – 20 % of maximum pressure
Injection Speed	Low to medium of maximum speed

However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.

PRODUCT PACKAGING

- 25 kg loose bag
- 25 kg stretch wrap on palletized

For further information, contact IRPC's Sales representative.

STORAGE

The resin should be stored in a dry location with good housekeeping practices during storage, transferring and handling. Process enclosures and adequate ventilation should be used to avoid excessive dust accumulation. Resin should be protected from direct sunlight, temperatures above 38°C (100°F) and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time. The container should be kept closed to prevent contamination. For the additional recommended storage conditions, please refer to SDS.

SAFETY

This product is not classified as hazardous material for more information please refer to safety data sheet.

RECYCLING

It is an undisputed fact that the product can be recycled or disposed of without any problem.

DISCLAIMER

The data indicated above are the results of IRPC's examinations, knowledge and correspond to the state of the art as of the date of publication and the data refers to the state of the related laws and regulations as of the date of issue. This information will expire after a break in delivery lasting more than 12 (twelve) months or in case of regulatory changes. This "Statement" is provided and subjected to IRPC's terms and conditions and IRPC reserves the right, in its sole discretion, to amend the product specification(s) at any time. This "Statement" is not intended and shall not be construed as specification, warranty, expressed or implied, or representation of any kind that IRPC would have any legal responsibility or liability. The applicability, accuracy, completeness, reliability, usability, availability, validity with respect to the data or information under this Statement and/or the suitability of IRPC's products cannot be guaranteed for any purpose. IRPC gives no guarantees or makes no warranties of any kind, express or implied, including, but not limited to, any warranties of merchantability, satisfactory quality, non-infringement or fitness for a particular purpose, whether arising by operation of law or otherwise. In the case that IRPC's products are used in combination with other materials, no liability admitted. When not utilized in combination with any third-party products, the information mentioned above refers only to IRPC's products. It is the customer's responsibility to inspect and test IRPC's products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer shall be responsible for the appropriate, safe and legal use, processing and handling of IRPC's products. IRPC shall not be liable for any false, inaccurate, inappropriate or incomplete data or information presented on this Statement. Please do not hesitate to ask IRPC for new information if needed. All terms and conditions regarding the supply of IRPC's products shall be subjected to IRPC's Policy. In the event that any dispute arises, IRPC's decision is final and not subject to appeal.



IRPC Public Company Limited | 555/2 Energy Complex, Building B, 6th Floor, Vibhavadi Rangsit Rd., Chatuchak, Bangkok 10900 THAILAND.
HTTPS://POLIMAXX.IRPC.CO.TH | TEL : +66(O) 765-7000